

Report Number :

BOMT18010289



Intertek India Private Limited

G3, Ground Floor, Akruti Corporate Park, LBS Marg, Opp: Naval Civilian Housing Colony, Kanjurmarg (West), Mumbai – 400 079 Tel : +91-22-67976900.,
Fax : 91-22-5503 1087

Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek.com.


TEST REPORT

NUMBER : BOMT18010289
DATE : 17-Feb-2018

APPLICANT : SWAYAM NIRYAT
A/803, Samprat - 2, Nr. Kiran Motors, Opp.
Rajpath Club, S.g. Highway, bodakdev,,
Ahmedabad, Gujarat, 380015, India
ATTN : Sanjay Tiwari

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE.

Applicant Provided Care Instructions :



Date Received/Date Test Started : 16 Feb 2018
Date Confirmation Received : -
Buyer Name : SASO
Style No :
Order No : -
Color : -
Fiber Content : 100% POLYESTER
Performance No. : SASO GSO 1829/2007
Vendor Name : Swayam Niryat
Buyer Name : SASO

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

CONCLUSION :

Fibre Identification/composition	M
Colour Fastness to Washing	M
pH Value	M
Labelling	*

NOTE:

M = MEETS REQUIREMENT,	F = FAILS TO MEET REQUIREMENT
* = REQUIREMENT NOT PROVIDED,	NA = NOT APPLICABLE
# = SEE REMARK,	C = CONFIRM LABEL
- = NOT PERFORMED	

NR = NOT REQUESTED

AUTHORIZED BY
FOR Intertek India Private Limited - [Mumbai]

INDIRA DEVADIGA
LAB MANAGER

TEST REPORT

NUMBER : BOMT18010289
DATE : 17-Feb-2018

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Fibre Identification/composition

SASO 781: 1994

Warp	Polyester	<u>Marked</u>
Weft	Polyester	
FIBRE COMPOSITION (ON FABRIC BASIS) :	100% Polyester	<u>Marked</u> 100% Polyester

2. Colour Fastness to Washing

AATCC 61: TEST NO 2A, 45 MIN MECHANICAL WASH AT 120°F, IN 0.15% AATCC WOB DETERGENT SOLUTION WITH 50 STEEL BALLS

Colour Change		4.0	<u>Requirement</u> 4 (Min.)
COLOUR STAINING	Acetate	4.0	4 (Min.)
	Cotton	4.0	
	Nylon	4.5	
	Polyester	4.5	
	Acrylic	4.5	
	Wool	4.5	
Self Staining		5.0	4 (Min.)

3. pH Value

SASO 2144

7.3	<u>Requirement</u> Direct contact with skin- 4.0 to 7.5
-----	--


4. Labelling

VISUAL

Fiber Content	Present	<u>Requirement</u> Present
Country of Origin	Present	
Language Written in Arabic Or English	Present	

TEST REPORT

NUMBER : BOMT18010289
DATE : 17-Feb-2018



END OF THE TEST REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Addressee in respect of this report and only accepts liability to the Addressee insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute.